

Introduction

2104.01.EN

This series of Technical Notes consider the importance of using GCCM* specific ASTM standards when selecting GCCM materials for use on erosion control projects:

The Problem:

GCCMs are unlike most geosynthetics as their properties change on hydration from flexible to rigid. Both the uncured (pre-set, soft and flexible) and cured (post-set, hardened and rigid) properties need to be reported to understand the GCCM capabilities in both deployment and in-service respectively.

GCCMs contain geosynthetic and cementitious materials, both of which possess very different physical properties. Geosynthetics are typically buried and their performance is often assessed according to their tensile strength, whereas hardened cementitious materials are often exposed and their performance is typically assessed according to their compressive strength, which is typically correlated with other key characteristics such as abrasion resistance, freeze thaw resistance and resistance to chemical attack.

GCCMs are the only geosynthetic to contain unset cementitious material and pre-existing geosynthetic test standards do not include methods for understanding the performance of the cementitious material contained within a GCCM. It is therefore important to test the properties of the cured cementitious material so that the behaviour of the GCCM as a hardened composite can be understood. It is also critical to ensure the cementitious material is cured at a water/powder ratio that is representative of field (in-service) hydration and not artificially controlled in the laboratory.



Figure 1. The change of GCCM properties from flexible to rigid on curing means that when assessing GCCM properties, appropriate test methods should be used to determine the cured, in-service GCCM cementitious layer performance.

The Solution:

Since 2015, the ASTM International Standards Organisation and its D35 Geosynthetics Committee has published a number of standards specifically for GCCMs to address the shortfalls in using pre-existing geosynthetic or concrete standards. These GCCM specific standards enable consistent, accurate reporting of essential GCCM properties.

They include:

- **ASTM D8364** 'Standard Specification for GCCM materials'
- **ASTM D8329** 'Standard Test Method for Determination of Water/Cementitious Materials Ratio for GCCMs and Measurement of the Compressive Strength of the Cementitious Material Contained Within'
- **ASTM D8058** 'Standard Test Method for Determining the Flexural Strength of a GCCM Using the Three-Point Bending Test'
- **ASTM D8030** 'Standard Practice for Sample Preparation for GCCM'

These standards have been created to ensure that repeatable testing and reporting of GCCM properties is conducted on specimens that have been prepared in a manner that is consistent with their use in the field, so the test results are representative of GCCMs installed in real-world operating conditions. Applying non-GCCM tests can result in properties that vary by an order of magnitude from field properties.

*Geosynthetic Cementitious Composite Mat

This Technical Note 3 focusses on the importance of using ASTM D8058 for determining the flexural strength of GCCMs.

ASTM D8058 GCCM Flexural Strength:

GCCMs behave as composite materials, they combine the benefits of geosynthetics and concrete. Broadly speaking, conventional geosynthetics are strong in tension and weak in compression, whereas concrete is strong in compression but weak in tension.

Flexural Strength testing of cured GCCMs provides the best overall indication of the in-service performance of a GCCM by compressing one surface while simultaneously extending the other and is considered the standard index test for this class of material.

The internationally recognised standard for flexural strength testing of GCCMs is ASTM D8058 'Standard Test Method for Determining the Flexural Strength of a GCCM Using the Three-Point Bending Test'.

What is ASTM D8058:

ASTM D8058 uses a constant rate of extension testing machine with a 3-point fixture set up to continuously measure the stress and displacement of a cured GCCM specimen as it is loaded to failure. By studying the results, ASTM D8058 enables the composite performance of a GCCM to be understood by determining both the Initial Flexural Strength (IFS), which is governed by the cementitious material, and the Final Flexural Strength (FFS), when the geosynthetic components fail.




Figure 2. ASTM D8058 Flexural Strength Testing of cured Concrete Canvas CC8™. Photo taken after the 1st crack of the cementitious material (IFS) and before geosynthetic failure (FFS).

An example stress/displacement graph generated by flexural testing of a GCCM to ASTM D8058 is presented in Figure 3 and demonstrates a semi ductile failure in 3 phases:

1. First, the initial elastic phase where the displacement is reversible. This phase always precedes the first crack of the cementitious material, which is the IFS. The specimen in Figure 3 has an IFS exceeding 4MPa
2. Second, the GCCM ruptures in a saw tooth pattern of progressive concrete failure and fibre loading
3. Finally, ultimate failure occurs as the geosynthetic fibres themselves reach their ultimate loading limit, which is the FFS.




Figure 3. Stress/displacement graph of Concrete Canvas CC5™ tested to ASTM D8058

After the IFS is reached and the cementitious material in the GCCM first cracks, its composite behaviour is changed as the fibres take up the load that was previously carried by the rigid concrete layer. The IFS of a GCCM may have a significantly lower strength than its FFS, which may not be recorded until very large deflections are reached. Such large deflections are unlikely to be seen in any typical application. Therefore when assessing the Flexural Strength of GCCMs, the primary index for comparison should be the Initial Flexural Strength. Specimens must be prepared in accordance with GCCM sample preparation standard ASTM D8030 and tested in accordance with ASTM D8058.

Note: ASTM D8030 'Standard Practice for Sample Preparation for GCCM' details the procedure for the hydration and curing of GCCM material for subsequent physical property testing. GCCMs are hydrated in the field by spraying or immersion, but immersion almost always occurs due to pooling of water on GCCM surfaces. Immersion will produce the highest water/cement ratio possible in the GCCM, resulting in the lowest in-service compressive strength and (according to BR331 - Design of Normal Concrete Mixes: second edition) the poorest durability of the cementitious material. It is critical that the performance of a construction material is assessed based on the worst-case area, as a failure will usually occur at the weakest point in the structure. It is therefore necessary to understand the in-service performance of GCCMs that have been hydrated by full immersion. Test specimens cured in accordance with ASTM D8030 are cured by immersion in hydration tanks for 24 hours.

Providing the GCCM has a waterproof backing layer, the semi ductile failure of GCCMs can have practical benefits, particularly in areas of differential settlements or ground heave, as the GCCM can crack and deform locally. The waterproof backing layer is typically more elastic and is therefore still protected by the protective cover layers of the composite, so the GCCM will continue to provide erosion protection under settlement. However if the GCCM does not have a waterproof backing layer, cracking in the cementitious material has the potential to allow water seepage.

Why use ASTM D8058:

Using ASTM D8058 to report the IFS of a GCCM can provide important information on the likely performance of the material in service, as there is a clear relationship between IFS and key performance criteria such as compressive strength, abrasion resistance (Figure 4) and freeze-thaw durability. IFS is used as the index test to determine resistance of the cementitious core of the GCCM to chemical immersion.

In terms of field performance, GCCMs with a lower IFS will tend to have a weaker cementitious layer and are more likely to disintegrate over time. A higher IFS is therefore preferable and ASTM D8058 3-point bending tests are used by GCCM manufacturers to check material quality as part of factory production control procedures.

A higher IFS demonstrates the cementitious material is well constrained in the GCCM and the water/cement ratio is controlled. Poor quality cement blends and high water/cement ratios would be reflected in a lower IFS. It is therefore important for GCCM manufacturers to report the IFS of their material when tested to ASTM D8058. This is defined in GCCM Specification Standard ASTM D8364, requiring all GCCM materials to have a minimum IFS of 3.5MPa at 24 hours from hydration. Concrete Canvas Ltd Quality Control procedure dictates that at 24 hours after curing, a minimum machine direction IFS of 4.0MPa is required.

24-hour IFS can also be used as part of Material Quality Assurance to verify that the material supplied to a project meets the specifications. This is a relatively inexpensive test that can provide an indication of cured GCCM performance in 24 hours, without the expense and wait for 28-day compressive strength results.

Recommendations:

Specifying a minimum GCCM Initial Flexural Strength to ASTM D8058 will ensure that the performance of the cementitious material within a GCCM will meet your requirements.

It is important not to accept only Final Flexural Strength results or test data conducted to different flexural strength test standards, as these standards often do not specify how a test specimen is hydrated allowing samples to be prepared in way that may give artificially high results which are representative of actual field performance. Test specimens must always be prepared to ASTM D8030.

Make sure the GCCM manufacturer can support their datasheets by providing appropriate test certificates from an independent test lab. BICS Laboratories Ltd have determined the flexural strength of Concrete Canvas® GCCMs to ASTM D8058. CC5™, CC8™ and CC13™ GCCMs all have a minimum 1-day Initial Flexural Strength of over 3.5MPa which is in compliance with GCCM Specification Standard ASTM D8364. Please see the [CC Spec Sheet to ASTM D8364](#) for details.




Figure 4. Comparison of ASTM D8058 Flexural Strength with abrasion resistance. The higher the IFS, the more resistant the GCCM to abrasion.